

M2V

HIGH-PERFORMANCE REFLECTIVE INSULATION

INSULATION | VAPOR BARRIER

A 8 mm reflective insulating vapor barrier consisting of two layers of air bubbles, laminated between a metallized polyethylene sheet and a white polyethylene sheet.

- **Installs quickly, easily and provides an excellent R-value**
- **Reduces condensation, air infiltration, and energy costs**

PRODUCT PURPOSE

Application	Insulation	
Building Part	Roofs	Walls
	Floors	Ceilings
	Other	

PRODUCT CHARACTERISTICS

Surface	Metallized polyethylene	
Underface	White polyethylene	
Installation Method	Stapled	Adhesive tape
Operating temperature	-45 °C to 82 °C (-50 °F to 180 °F)	

PACKAGING

Code	Width		Length		Gross area	
	m	ft	m	ft	m²	ft²
55044	2.44	8	38.10	125	92.96	1000
55050	2.44	8	19.05	62.50	46.48	500
55041	1.22	4	38.10	125	23.23	250
55042	1.22	4	19.05	62.50	23.23	250
55020	1.22	4	3.81	12.50	4.65	50
55251	1.83	6	38.10	125	10.98	750
55211 (V2M)	1.22	4	38.10	125	23.23	250
55045 (V2M)	2.44	8	19.05	62.50	46.48	500
55216 (V2M)	1.83	6	38.10	125	10.98	750
55046 (Water heater insulation jacket 60 gal.)	Complete kit to cover a 60 gallons water heater tank					
55047 (Water heater insulation jacket 40 gal.)	Complete kit to cover a 40 gallons water heater tank					

M2V




PROPERTIES

Properties	STANDARDS	M2V
Nominal tickness	-	8 mm (5/16 in)
Emissivity	-	0.06
Reflectivity	-	0.94
Compressive strenght	-	414kN/m ² (60.05 lb/in ²)
Tensile Strength	CAN/CGSB-51.33-M89	3.7 N/mm (21.13 lb/in)
Water vapour permeance	ASTM E96	Conforms type 1
Linear Shrinkage	-	None
Flame spread	ASTM E84	10 (Class 1 / class A)
Smoke development	ASTM E84	110 (Class 1 / class A)
Resistance to fungi and bacteria	-	Does not promote growth
Electric conductivity	-	None
Corrosivity, 200 °F (93 °C) - 7 days	-	Pass
Pliability	CAN / CGSB-51.33 M89	No cracking

(Nominal values)

REFLECTO-FOIL REFLECTIVE INSULATION PRODUCTS ARE TESTED ACCORDING TO ASTM C1224, ASTM C1363 AND ASTM C518 STANDARDS

INSTALLATION

Storage	Store rolls upright, in a dry and heated place to limit the risk of condensation.		
Complementary Products	ADHESIVE TAPE ALUMINUM		ADHESIVE TAPE METALLIZED
	ADHESIVE TAPE WHITE VINYL		
Tools Required	 Knife		Tape measure
			Stapler

Surface Preparation	All cracks and surface holes should be repaired before installing an HIGH-PERFORMANCE REFLECTIVE INSULATION product. If there is an existing vapor barrier, it must be removed or torn to avoid condensation problems.
Installation	<p>M2V can be stapled, nailed, screwed, glued and threaded. The installation method of these products may have an impact on their efficiency; it is therefore important to know the best installation methods recommended by REFLECTO-FOIL. Furthermore, since REFLECTO-FOIL reflective insulation is also a 100% vapour barrier, it must be installed on the warm side of the assembly, according to the construction standards in your area.</p> <p>Moreover, the use of SPACER STRIPS or wood furring strps is highly advised. They create an air space between the REFLECTING INSULATION and the surface to be insulated to easily obtain maximum insulating value at a low price. The recommended air space should be between 0.5 in to 2 in (1.25 cm to 5 cm).</p>
Tricks / Tips	To minimize air infiltration and humidity transfer, ensure that the HIGH-PERFORMANCE REFLECTIVE INSULATION is not punctured and the insulation system is waterproof. All holes and junctions between two insulation materials must be sealed with REFLECTO-FOIL ADHESIVE TAPE or with a suitable sealant.